



# Hoffman PVC V0-202 NATURAL

Hoffman Plastic Compounds Inc. - Flexible Polyvinyl Chloride

## General Information

### General

Appearance	• Natural Color
Forms	• Pellets

## Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.43		ASTM D792
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	1700	psi	ASTM D412
Tensile Strength (Break)	2500	psi	ASTM D412
Tensile Elongation (Break)	250	%	ASTM D412
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	93		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-10.0	°F	ASTM D746

### Additional Information

Cell Class (ASTM D-2287-81): PVC 66603  
 Durometer Hardness, ASTM D2240, Shore A, instantaneous: 93  
 Durometer Hardness, ASTM D2240, Shore A, 10 second delay: 88