

EVOPRENE G 991

Alphagary - Styrene Ethylene Butylene Styrene Block Copolymer

General Information

General

Features	• Block Copolymer
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density (73°F)	1.00	g/cm ³	ISO 2781
Flow Rating (356°F)	17	kg/cm ²	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Abrasion Resistance (73°F)	130	mm ³	ISO 53516
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain, 73°F)	261	psi	ISO 37
Tensile Stress (300% Strain, 73°F)	464	psi	ISO 37
Tensile Stress (Yield, 73°F)	1450	psi	ISO 37
Tensile Elongation (Break, 73°F)	750	%	ISO 37
Tear Strength (73°F)	171	lbf/in	ISO 6383
Compression Set			ISO 815
73°F, 72 hr	23	%	
158°F, 22 hr	36	%	
212°F, 22 hr	52	%	
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A, 73°F)	63		ISO 868
Additional Information	Nominal Value	Unit	Test Method
UV Resistance - Xenon Arc	Excellent		Internal Method