



NOVALAST® 6001

NOVA Polymers, Inc. - Thermoplastic Vulcanizate

General Information

General

Features	• Chemical Resistant	• Food Contact Acceptable	• Good Colorability
Forms	• Pellets		
Processing Method	• Blow Molding	• Extrusion	• Injection Molding

Properties¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.955		ASTM D792

Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Break)	950	psi	ASTM D412
Tensile Elongation (Break)	400	%	ASTM D412
Tear Strength ²	172	lbf/in	ASTM D624
Compression Set			ASTM D395
77°F, 22 hr	27	%	
158°F, 22 hr	36	%	
212°F, 22 hr	48	%	

Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	63		ASTM D2240

Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-50.0	°F	ASTM D746

Processing Information

Injection	Nominal Value	Unit
Processing (Melt) Temp	390	°F

Notes

¹ Typical properties: these are not to be construed as specifications.

² Die C