

# SKYPEL® P147DF

## SK Chemicals - Thermoplastic Polyester Elastomer

### General Information

#### Product Description

SKYPEL P147DF is a thermoplastic polyester elastomer resin superior heat resistance. SKYPEL P147DF with a medium 47D hardness based on shore D scale is widely used for injection molding and extrusion applications. And SKYPEL P147DF is also available to overmold TPU, PC, ABS, PC/ABS alloys.

#### General

Features	• High Heat Resistance
Forms	• Pellets
Processing Method	• Extrusion • Injection Molding

### Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.18		ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	18	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.016	in/in	ASTM D955
Water Absorption (24 hr)	1.4	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>2</sup>			ASTM D638
5.0% Strain, 0.0787 in, Injection Molded	626	psi	
10% Strain, 0.0787 in, Injection Molded	1140	psi	
Tensile Strength <sup>2</sup> (Break, 0.0787 in, Injection Molded)	2990	psi	ASTM D638
Tensile Elongation <sup>2</sup>			ASTM D638
Break, 0.0787 in, Injection Molded	> 400	%	
Flexural Modulus <sup>3</sup>	14900	psi	ASTM D790
Elastomers	Nominal Value	Unit	Test Method
Tear Strength <sup>4</sup> (0.0787 in)	514	lbf/in	ASTM D624
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.250 in)	No Break		ASTM D256
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	< 47		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	185	°F	ASTM D648
Peak Crystallization Temperature (DSC) <sup>5</sup>	421	°F	ASTM D3418
Additional Information	Nominal Value	Unit	Test Method
Resilience <sup>6</sup>	54	%	ASTM D2632

### Processing Information

Injection	Nominal Value	Unit
Rear Temperature	428	°F
Middle Temperature	446	°F
Front Temperature	446	°F
Nozzle Temperature	455	°F
Mold Temperature	104	°F

## SKYPEL® P147DF

### SK Chemicals - Thermoplastic Polyester Elastomer

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	401	°F
Cylinder Zone 3 Temp.	428	°F
Cylinder Zone 5 Temp.	428	°F
Melt Temperature	437	°F
Die Temperature	428	°F

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> Type IV, 2.0 in/min

<sup>3</sup> 0.051 in/min

<sup>4</sup> 2.0 in/min

<sup>5</sup> Heating rate 10°C/min.

<sup>6</sup> Vertical rebound