

Zythane® 7080A

Alliance Polymers & Services - Thermoplastic Polyurethane Elastomer (Polyether)

General Information

Product Description

Zythane 7080A is a polyether-based TPU specifically formulated for extrusion applications with ease of processing. It exhibits excellent abrasion resistance and toughness and has good hydrolytic stability, oil, fuel and solvent resistance. It is supplied uncolored in pellet form.

Typical Applications:

Zythane 7080A applications include among others FDA applications, cable sheathing, spiral and pneumatic tubing, film, irrigation hoses, conveyor hoses, fire hoses, hydraulic hoses, cable jacketing, flat flex cables, automotive sensor cables.

General

Features	<ul style="list-style-type: none"> Abrasion Resistant Fuel Resistant 	<ul style="list-style-type: none"> Good Toughness Hydrolytically Stable 	<ul style="list-style-type: none"> Oil Resistant Solvent Resistant
Uses	<ul style="list-style-type: none"> Automotive Applications Cable Jacketing 	<ul style="list-style-type: none"> Hose Tubing 	
Agency Ratings	<ul style="list-style-type: none"> FDA 		
Appearance	<ul style="list-style-type: none"> Colorless 		
Forms	<ul style="list-style-type: none"> Pellets 		
Processing Method	<ul style="list-style-type: none"> Extrusion 	<ul style="list-style-type: none"> Injection Molding 	

Properties¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.11		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Taber Abrasion Resistance	23.0	mg	ASTM D1044
Abrasion - DIN	15	mm ³	DIN 53516
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	580	psi	ASTM D412
Tensile Stress (300% Strain)	1020	psi	ASTM D412
Tensile Strength (Break)	5080	psi	ASTM D412
Tensile Elongation (Break)	610	%	ASTM D412
Tear Strength ²	560	lbf/in	ASTM D624
Compression Set			ASTM D395B
75°F, 22 hr	23	%	
158°F, 72 hr	37	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	80		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-40.0	°F	DSC
Vicat Softening Temperature	194	°F	ASTM D1525
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.04 in		HB	
0.06 in		HB	
0.12 in		HB	

Zythane® 7080A

Alliance Polymers & Services - Thermoplastic Polyurethane Elastomer (Polyether)

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	185	°F
Drying Time	4.0	hr
Rear Temperature	347	°F
Middle Temperature	374	°F
Front Temperature	401	°F
Nozzle Temperature	401 to 410	°F
Processing (Melt) Temp	392 to 401	°F
Mold Temperature	77 to 140	°F
Back Pressure	72.5 to 145	psi
Screw Speed	60 to 200	rpm
Clamp Tonnage	3.0 to 5.0	tons/in ²

Injection Notes

Injection Speed: >.4 in/sec

Extrusion	Nominal Value	Unit
Drying Temperature	185	°F
Drying Time	4.0	hr
Cylinder Zone 1 Temp.	347	°F
Cylinder Zone 2 Temp.	374	°F
Cylinder Zone 3 Temp.	401	°F
Die Temperature	401	°F

Extrusion Notes

Gate Temperature: 205°C (401°F)

Notes

¹ Typical properties: these are not to be construed as specifications.

² Die C