

# Zythane® 8090AM

## Alliance Polymers & Services - Thermoplastic Polyurethane Elastomer (Polyester)

### General Information

#### Product Description

Zythane 8090AM is a FDA polyester--based TPU specifically formulated for injection molding applications. It exhibits excellent abrasion resistance and toughness and has good hydrolytic stability, oil, fuel and solvent resistance. It is supplied uncolored in clear pellet form.

Typical Applications:

Zythane 8090AM applications include among others spiral and pneumatic tubing, round and V belting, blow molded bellows.

#### General

Features	<ul style="list-style-type: none"> <li>Abrasion Resistant</li> <li>Fuel Resistant</li> <li>Good Toughness</li> </ul>	<ul style="list-style-type: none"> <li>Halogen Free</li> <li>Hydrolytically Stable</li> <li>Oil Resistant</li> </ul>	<ul style="list-style-type: none"> <li>Solvent Resistant</li> </ul>
Uses	<ul style="list-style-type: none"> <li>Tubing</li> </ul>		
Agency Ratings	<ul style="list-style-type: none"> <li>FDA</li> </ul>		
Appearance	<ul style="list-style-type: none"> <li>Colorless</li> </ul>		
Forms	<ul style="list-style-type: none"> <li>Pellets</li> </ul>		
Processing Method	<ul style="list-style-type: none"> <li>Injection Molding</li> </ul>		

### Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.23		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Taber Abrasion Resistance	23.0	mg	ASTM D1044
Abrasion - DIN	22	mm <sup>3</sup>	DIN 53516
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	1600	psi	ASTM D412
Tensile Stress (300% Strain)	3340	psi	ASTM D412
Tensile Strength (Break)	6240	psi	ASTM D412
Tensile Elongation (Break)	560	%	ASTM D412
Tear Strength <sup>2</sup>	728	lbf/in	ASTM D624
Compression Set			ASTM D395B
75°F, 22 hr	23	%	
158°F, 72 hr	38	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A	90		
Shore D	41		
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-24.0	°F	DSC
Vicat Softening Temperature	270	°F	ASTM D1525
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.04 in	HB		
0.06 in	HB		
0.12 in	HB		

# Zythane® 8090AM

Alliance Polymers & Services - Thermoplastic Polyurethane Elastomer (Polyester)

## Processing Information

Injection	Nominal Value	Unit
Drying Temperature	185	°F
Drying Time	4.0	hr
Rear Temperature	365	°F
Middle Temperature	392	°F
Front Temperature	401	°F
Nozzle Temperature	401 to 419	°F
Processing (Melt) Temp	401 to 419	°F
Mold Temperature	77 to 140	°F
Back Pressure	72.5 to 145	psi
Screw Speed	60 to 200	rpm
Clamp Tonnage	3.0 to 5.0	tons/in <sup>2</sup>

### Injection Notes

Injection Speed: >.4 in/sec

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> Die C